

B^EZILLO[®]

SUPERIOR QUALITY PRODUCTS.

CLARIPOX W



BEZILLO CLARIPOX W

PRODUCT DESCRIPTION

Bi-component Claripox W system with medium viscosity and high reactivity. Thanks to the low tendency to darken the materials (also with low density structure) and high UV resistance, it is recommended for the surface treatment of white/light color marbles, granites and natural stones.

INSTRUCTIONS OF USE

In order to maximize product performances, the following instructions should be followed:

- The two components must be carefully weighed and mixed until a homogeneous system is obtained. If possible, try to avoid the entrapment of air bubbles during mixing. After withdrawal, the containers must be hermetically closed.
- Before product application, the surface of the stone must be dried and clean. Hardening process of the product in thin film is optimal at around 40°C.

STORAGE AND SAFETY

If stored in original containers in dry and clean environment, the product can be used up to 1 year from production date. The product should never be exposed to direct sunlight. In case of crystallization, heat the product until the original transparency is achieved and, after mixing, return it back to standard ambient conditions.

The product must be always used in aerated ambient wearing the suitable Personal Protective Equipment. Before use, Material Safety Data Sheets must be carefully looked up.

Technical information provided in the present document are given in good faith and derive from accurate laboratory tests. Gems Italia will never take charge of damages to people and/or objects arising from an improper use of the product.

ADVANTAGES

-  ...▪ Extra clear transparent epoxy resin with low viscosity
-  ...▪ Very low yellowing to sunrays
-  ...▪ Recommended for indoor/outdoor use
-  ...▪ Mixing ratio 3+1
-  ...▪ Colorable with bezillo universal colorant paste
-  ...▪ Used by professionals

DISCLAIMER

This information is true and accurate to the best of our knowledge and belief, but since the circumstances of use and any labour required are out of our control, the end user must verify beforehand that the product is appropriate for his particular application. No responsibility can be accepted, and no warranty can be provided by our Representatives, Agents, or Distributors. The end user should make sure he has read our most recent material and that the products are sold in accordance with our Standard Conditions of Sale.

BEZILLO CLARIPOX W

PROPERTIES OF SINGLE COMPONENTS

	Resin	Hardener
Appearance	Transparent	Transparent
Density 25°C	1,10-1,15 g/ml	0,95-1,00 g/ml
Viscosity 25°C	750-950 mPas	40-100 mPas
Gardner Color	-	Max 1

PROPERTIES OF THE SYSTEM

	Quantity	Drying time
Pot Life 25°C	125 cc	15m - 25m
Gel Time 25°C	Film 100-150µm	2h 20m - 2h 50m
Gel Time 40°C	Film 100-150µm	1h 00m - 1h 10m
Mixing Ratio (weight) - A : B	100 : 37	
Mixing Ratio (volume) - A : B	100 : 42-43	
Viscosity 25°C	200-400 mPas	





BETON STONE SOLUTIONS INDIA PVT LTD

+91 99301 28291

info@betonstonesolutions.com | www.betonstonesolutions.com

Italy - Headquarter

Via Monte Cengio,
11/0 36073, Cornedo
Vicentino (VI) Italy.

United Arab Emirates

P.O. Box
239697,
Dubai UAE.

India - Mumbai

B/2, Amrat Niwas, 15th
Sarojini Road, Ville Parle
(W), Mumbai - 400056, India.

India - Hyderabad

Plot No.18, Saibabanagar
Colony, Tellapur, R.C. Puram,
Sangareddy, Hyderabad, India.